



White Grease 3

A medium viscosity, calcium based multi-purpose grease. Excellent lubricating properties that protect against salt-water corrosion and is resistant to heat and cold conditions.



Part N°: 50073 (SWGIII) - 500ml aerosol

Features & Benefits

- Calcium based - Impervious to water, unlike lithium based competitors
- Silicone free - Body shop safe
- Excellent adhesion - Will not run or slump
- Viscostatic - Retains properties over wide temp range
- Contains additives to increase long term stability, improve oxidation resistance and corrosion inhibition
- Slotted cap with extension nozzle

Applications

Spray White Grease III is water resistant and weak acid and alkaline solutions so is very suitable for centralised lubrication systems.

It is most commonly used during vehicle servicing, for the lubrication of door locks, hinges and check straps. It is also widely used for other areas, such as seat runners, brake and clutch pedals, bonnet catches and hinges, choke and throttle linkages, sun roof runners, suspension bushes, leaf springs and window regulators. Since it is calcium based, SWGIII will not swell nylon, unlike lithium, which means that it can be safely used on areas like sun roof runners and runners for curtain side trucks.

Instructions

1. Shake well before use.
- 2.. For difficult to reach places use the extension tube.



Technical Information

Part N°:	50073	Corrosion protection:	0 -0 (DIN 51 802) EMCOR test
Description:	Spray White Grease III	Corrosion protection:	2-2 (DIN 51 802) with 3% NaCl
Shelf Life:	30 months	Copper Corrosion:	1-100 (DIN 51 811)
VOC:	527g/l	Water resistance:	0 -90 (DIN 51 807-1)
Stock Code:	SWG III	Oxidation stability:	<350 hPa (DIN 51 808)
Customs Tariff Code:	3403 19 99	Four Ball welding load:	:2600N (DIN 51 350)
SDS:	Yes	Dropping point:	>250°C (IP 396/93)
Temp resistance:	-20°C to 160 °C	Worked penetration:	300-320 (DIN ISO 2137)
NGLI grade:	1-2 (DIN 51818)	Unworked penetration:	270-300 (DIN ISO 2137)
Acid / alkali resistance:	Good for weak acids and mild alkali conditions	Work resistance:	<30 (DIN ISO 2137)
		Flow pressure 20C:	<80 hPa (DIN 51805)
		-30C:	<1350 hPa (DIN 51805)



SDS available on www.kenturope.com

Terms and Conditions

No part of this publication may be reproduced, transmitted or stored, electronically, mechanically or photocopied without the prior permission of KENT (United Kingdom) Ltd. This data sheet and its contents (the "Information") belong to the KENT (United Kingdom) Ltd or are licensed to it. No license is granted for the use of it other than for information purposes in connection with the products to which it relates. No license of any intellectual property rights is granted.

The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but the Group assumes no responsibility for its accuracy or completeness, any error from or omission in it nor for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including

liability resulting from negligence or where the Group was aware of the possibility of such loss or damage arising) is excluded. This will not operate to limit or restrict the Group's liability for death or personal injury resulting from its negligence KENT is the trading name of KENT (United Kingdom) Ltd

Registered Office: Amber House, Showground Road, Bridgewater, Somerset, United Kingdom, TA6 6AJ
All rights reserved.

KENT (United Kingdom) Ltd, Forsyth House, Pitreavie Drive, Pitreavie Business Park, Dunfermline, Fife, KY11 8US
Tel : 0800 136925 or 01383 723344 between 08:30-17:30 Monday-Thursday, 09:00-15:00 on Fridays.
For out of hours queries please **Fax** us on 01383 735829 or **Email:** kentinfo.uk@kenturope.com

Rev: 17/3/2017