



# Waxcoat - 1L Bulk



## Features

- Bulk packaging
- Suitable for use with fresh paint
- Easy to apply
- Compatible with GSH gun
- Medium viscosity
- Good adherence to common substrates

## Application Method

Waxcoat in 1 litre bulk tin is a specially developed cavity wax spray. It will provide a final layer of protection against water and other contaminants such as road salt, which will cause rust and other damage in out of sight areas within the vehicle. As its name suggests, it leaves a thick film of concentrated wax to prevent these contaminants attacking the metalwork. Waxcoat is ideal for doors, Bonnets, Boot lids, Tailgates, box sections, sill interiors, boot floors, foot wells and for rust protection of metal plates.

## Instructions for use

Waxcoat is applied by screwing the Kent Syphon gun (GSH), commonly used with the Toughcoat range, to the top of the canister, attaching an airline, and spraying on to the required surface.

When used to coat the more inaccessible areas, the use of an extension nozzle on the gun, (that can be supplied separately) greatly assists the operation.

Part N°	Description	Packaging
84465	Waxcoat (CWX-1L)	1 litre tin
34483	Syphon Gun (GSH)	1 piece
84466	Extension Nozzle (GSH-EXT)	1 piece
86172	HV EXTENSION TUBE	1 piece

## Benefits

- Cost effective solution
- Use with confidence
- Saves time
- Easy to apply
- Penetrates before drying
- Can be used throughout vehicle

1. Where possible, ensure surface to be coated is clean, dry and de-greased using KENT Acrysol or KENT Speedy 500
2. Shake tin well before use.
3. Attach KENT syphon gun to the Waxcoat container, ensuring that the gun is screwed on tightly
4. Attach gun to a suitable compressed air feed.
5. If applying into difficult to access areas, attach the extension nozzle onto the syphon gun
6. Spray product and build up thickness as required
7. Can be used on recently painted surfaces. Do not spray on engine, brakes or exhaust
8. If necessary, remove excess Waxcoat with KENT Acrysol or KENT Speedy 500



## Technical Information

<b>Part Number</b>	84465 Waxcoat 1 Litre (CWX-1L)	<b>Density:</b>	0.87 ± 1.02kg/L (DIN 51757)
<b>Part Number</b>	34483 Syphon Gun (GSH)	<b>Rec. coat depth:</b>	~ 100 microns wet /~ 50 microns dry
<b>Part Number</b>	84466 Extension Nozzle (GSH-EXT)	<b>Tack Free</b>	10-15 mins *
<b>Part Number:</b>	86172 HV Extension tube (HV Tube)	<b>Full drying time</b>	2-6 hours *
<b>Custom Tariff Code</b>	2715 00 00	<b>Salt spray test:</b>	Rust -> Ri 0 (DIN 53210)
<b>Shelf Life</b>	30 months	<b>(DIN 50021 1000 hrs)</b>	Blistering -> m0/g0 (DIN 53209)
<b>Selling Unit</b>	Each	<b>Op. Temp</b>	-30 to 80c
<b>Solids</b>	49-54% (DIN 53215)	<b>Consistency</b>	High viscosity, tacky brown liquid
<b>Flashpoint</b>	>39° C (ASTM 1320-67)	<b>VOC:</b>	394g/Litre
<b>Viscosity</b>	50 ± sec (Ford DIN cup nr 4)	* Dependent on temp/humidity & coat depth	
<b>Coverage:</b>	1 litre per 10 m <sup>2</sup>	<b>Base:</b>	Modified Petrolatum, Sulfonates, oil, solvents pigment and additives

**VOC Markings:** 2004/42/IIB(e)(840)394



**SDS available on [www.kenturope.com](http://www.kenturope.com)**

### Terms and Conditions

No part of this publication may be reproduced, transmitted or stored, electronically, mechanically or photocopied without the prior permission of KENT (United Kingdom) Ltd. This data sheet and its contents (the "Information") belong to the KENT (United Kingdom) Ltd or are licensed to it. No license is granted for the use of it other than for information purposes in connection with the products to which it relates. No license of any intellectual property rights is granted.

The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but the Group assumes no responsibility for its accuracy or completeness, any error from or omission in it nor for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including

liability resulting from negligence or where the Group was aware of the possibility of such loss or damage arising) is excluded. This will not operate to limit or restrict the Group's liability for death or personal injury resulting from its negligence KENT is the trading name of KENT (United Kingdom) Ltd

**Registered Office:** Amber House, Showground Road, Bridgewater, Somerset, United Kingdom, TA6 6AJ  
All rights reserved.

**KENT (United Kingdom) Ltd, Forsyth House, Pitreavie Drive, Pitreavie Business Park, Dunfermline, Fife, KY11 8US**  
**Tel :** 0800 136925 or 01383 723344 between 08:30-17:30 Monday-Thursday, 09:00-15:00 on Fridays.  
For out of hours queries please **Fax** us on 01383 735829 or **Email:** [kentinfo.uk@kenturope.com](mailto:kentinfo.uk@kenturope.com)

Rev: 7/3/2017