



Transparent Waxcoat

A wax based coating, providing excellent anti-corrosion properties for cavity areas or surfaces needing rust protection



TWB Transparent 1 Litre: 86160
TWA Transparent Aerosol 500ml: 86161

Features

- Excellent Corrosion resistance
- Self-Healing properties
- High penetrating ability
- Low odour
- No dripping, one hour after application
- Good adhesion

Applications

- General automotive in cavity areas such as doors, bonnets, cross members, reinforcements
- Bus & Coach work
- Trailer & Caravan work
- General metalwork

Dry times

100 micron liquid layer will be touch dry in 105 minutes and completely dry in 5 hours.

100 micron aerosol layer will be touch dry in 105 minutes and completely dry in 3½ hours.

Benefits

- Protects the treated area or parts against corrosion from the environment
- Resists damage, provides long lasting protection
- Penetrates and coats difficult to reach areas
- Pleasant to use
- Can be used with confidence
- Can be used throughout vehicle

Instructions

Shake the product thoroughly before use. Surfaces to be treated must be clean, dry, rust-free and grease-free; if necessary use Acrysol to clean and prepare surfaces.

The liquid can be applied by light airless spray equipment, or using an air-line fed gun or pressure pot gun with an air pressure of 3 to 6 bar. Brushing or dipping can also be used to apply the liquid.

Apply the aerosol in even strokes, building the desired layer thickness.

NB Product remains soft and sticky to the touch, this is a characteristic of the wax coating.



Technical Information

Description:	Transparent Waxcoat	Customs Tariff Code:	3824 9097
Shelf life:	24 Months	SDS:	Yes
Selling Unit:	Each	VOC: 1L Liquid	499G/L
Hazard (Aerosol):	Extremely Flammable	VOC: Aerosol	560G/L
Product colour:	Transparent (Milky)	Bend Test (DIN 53152 +70C):	No cracks, no loss of adhesion
Packaging:	1Litre and 500ml Aerosol	Bend Test (DIN 53152 -30C):	No cracks, no loss of adhesion
Label codes:	11 Aerosol; 28 Liquid	Cured Resistance:	water, salt spray, oil, soft bases and acids
Storage temp:	10C to 30C.	Salt spray test (DIN 50021 Ri 0)	Liquid >1000 hours at 100 micron dry layer Aerosol >720 hours at 50 micron dry layer
Temp Resistance:	-25C to +180C (cured)		
Viscosity (1L liquid):	DIN 53211 Cup 4mm 20 to 30 seconds		
Density (1L Liquid):	Ca 0.85 Kg/Litre		
Density (Aerosol):	Ca 0.72 Kg/Litre		



SDS available on www.kenturope.com

Terms and Conditions

No part of this publication may be reproduced, transmitted or stored, electronically, mechanically or photocopied without the prior permission of KENT (United Kingdom) Ltd. This data sheet and its contents (the "Information") belong to the KENT (United Kingdom) Ltd or are licensed to it. No license is granted for the use of it other than for information purposes in connection with the products to which it relates. No license of any intellectual property rights is granted.

The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but the Group assumes no responsibility for its accuracy or completeness, any error from or omission in it nor for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including

liability resulting from negligence or where the Group was aware of the possibility of such loss or damage arising) is excluded. This will not operate to limit or restrict the Group's liability for death or personal injury resulting from its negligence KENT is the trading name of KENT (United Kingdom) Ltd

Registered Office: Amber House, Showground Road, Bridgewater, Somerset, United Kingdom, TA6 6AJ
All rights reserved.

KENT (United Kingdom) Ltd, Forsyth House, Pitreavie Drive, Pitreavie Business Park, Dunfermline, Fife, KY11 8US
Tel : 0800 136925 or 01383 723344 between 08:30-17:30 Monday-Thursday, 09:00-15:00 on Fridays.
For out of hours queries please **Fax** us on 01383 735829 or **Email:** kentinfo.uk@kenturope.com

Rev: 21/3/2017