



Toughcoat

Toughcoat is a paintable, tough, hard, durable stone chip finish, which also works as sound deadening coating.



Features

- One Coat Coverage
- Fast Paint over
- Replicates most OEM finishes
- 3 colours available
- High build formula
- Stone chip and under body coating in one
- Plastic Bottle
- Sandable
- High solids – 60%
- IR drying possible

Benefits

- Saves time and money
- Lightweight formula
- Professional repair
- Right colour for job
- Covers welds and seams
- Reduced inventory
- Lighter and stronger than metal Shutz style tins
- Can blend texture
- Fully VOC compliant

Part No.	Description	Packaging
86721	Black	1L bottle
86722	Grey	1L bottle
86723	White	1L bottle

Application

Toughcoat is a paintable, tough, hard, durable stone chip finish, to protect vehicle body panels from corrosion, salt, humidity and stone chip damage. It offers fast paint over, single coat application and replicates the OEM finish found on most vehicles. It is available in Black, Grey and White.

Toughcoat can be used on all under surfaces of the vehicle such as wheel arches and, boot and floor Pans. Due to sound deadening characteristics also applicable as coating for inner parts and motor compartment.

Due to its ability to be over painted it is also ideal as a lower body protector against stone and gravel chips and is therefore the solution for the protective finish found on sill panels and front and rear lower panels.

Instructions

1. Can be used on suitably prepared bare metal (for over-coating aluminium, use Etch primer first) and original paint surfaces.
2. Thoroughly clean and degrease old paint surfaces, wet flat with 400 grit paper, for bare metal use 180 grit paper.
3. Wipe entire area with Kent Acrysol and allow to dry.
4. Shake bottle thoroughly before use.
5. Apply with KENT Aqua Gun (86190) or Shutz Gun (34483), adjusting air pressure to achieve required finish, allow approx. 10-15 mins between coats for solvent to flash off when building a thick coat.
6. Clean gun thoroughly after use

Over-painting for best results a use of a primer is recommended.



Technical Information

Part N°:	86721 – 86722 – 86723	Max. Coat Depth:	100 - 150 microns
Colour:	Black – Grey – White	Wet on Wet:	Only with 2k acrylic paint
Shelf Life:	24 months	Op. Temp:	-20°C to +90°C
Selling Unit:	EA	Working pressure:	1 – max. 5 Bar
VOC:	478 g / Litre (Black)	Touch Dry:	15 minutes
VOC:	465 g / Litre (Grey)	Flash off:	10 – 15 minutes
VOC:	460 g / Litre (White)	Drying time:	30 minutes (at 80° C) 2 hours (at 20° C)
Stock Code:	TCB4, TCG4, TCW4		
Customs Tariff Code:	32089091		
SDS:	Yes		
Replacing Product:	Toughcoat 3		
Resin Base:	Alkyd based		

VOC marking: 2004/42/IIB(e)(840)478 - BLACK
2004/42/IIB(e)(840)465 - GREY
2004/42/IIB(e)(840)460 - WHITE



SDS available on www.kenturope.com

Terms and Conditions

No part of this publication may be reproduced, transmitted or stored, electronically, mechanically or photocopied without the prior permission of KENT (United Kingdom) Ltd. This data sheet and its contents (the "Information") belong to the KENT (United Kingdom) Ltd or are licensed to it. No license is granted for the use of it other than for information purposes in connection with the products to which it relates. No license of any intellectual property rights is granted.

The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but the Group assumes no responsibility for its accuracy or completeness, any error from or omission in it nor for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including

liability resulting from negligence or where the Group was aware of the possibility of such loss or damage arising) is excluded. This will not operate to limit or restrict the Group's liability for death or personal injury resulting from its negligence KENT is the trading name of KENT (United Kingdom) Ltd

Registered Office: Amber House, Showground Road, Bridgewater, Somerset, United Kingdom, TA6 6AJ
All rights reserved.

KENT (United Kingdom) Ltd, Forsyth House, Pitreavie Drive, Pitreavie Business Park, Dunfermline, Fife, KY11 8US
Tel : 0800 136925 or 01383 723344 between 08:30-17:30 Monday-Thursday, 09:00-15:00 on Fridays.
For out of hours queries please **Fax** us on 01383 735829 or **Email:** kentinfo.uk@kenturope.com

Rev: 2/3/2017