



Ultra Plastic

Ultra Plastic has high filling and non-sagging characteristics and has excellent adhesion on a variety of plastic substrates.

Features & Benefits

- Uniform, fine creamy consistency – can be applied with minimum mess or wastage
- High filling and non-sag properties – can fill large areas in one operation
- Fast hardening – improves throughput in workshop
- Excellent sandability – ensures a fine, smooth finish
- Good adhesion on plastic and metal – repair will not delaminate from substrate
- Resistant to fuel, water, mineral oils and solvents – excellent durability once hardened and solvents



P/N	Product	S/C	Content	Packaging
86958	Ultra Plastic White / Grey	PUPB21	1000 g	Can

Application

KENT Ultra Plastic is for use by body shop professionals to level dents, scratches and depressions on automotive plastics and to provide an excellent finish to plastic repairs. Suitable for filling layers between 5 to 10 mm thick (dependent on size of area). Always use a mixing pallet, this minimises inclusion of air and reduces risk of contamination from other products. Use KENT Spray Guide to detect imperfections in final work.

Instructions

1. Thoroughly clean surface using KENT Plastic Prep (KPP), ensuring all other coatings are removed.
2. Add 2 - 4% of red hardener paste to 100g of beige filler on a mixing plate.
3. Mix both compounds with spatula using a sweeping 'figure of eight' motion until a uniform pinkish colour is achieved. The mixture can be worked for 2 to 6 minutes depending on ambient temperature.
4. Apply mixture to surface using spatula.
5. After 15 to 30 minutes (depending on ambient temperature) the hardened filler can be sanded.
6. Compatible with all leading automotive refinish paint systems.



Technical Information

General Info:

Consistency:	Smooth non-sag paste
Base material:	Polyester
Colour:	White / Grey
Odour:	Characteristic peroxide
Shelf Life (months):	12
Customs Tariff Code:	3214 10 90
VOC:	150 g/l
Accessories:	Spatula in lid & hardener
Pieces per unit:	1

Pot life:	4 - 5 min
Mixing ratio:	98% filler / 3-4% Hardener
Working time:	approx. 3 min
Drying time:	15 - 30 min
Wet on wet:	No
Shore D hardness:	79-80
Specific gravity:	2 g/cm ³
Application temperature (min.):	15 °C
Application temperature (max.):	30 °C
Temperature resistance (max.):	100 °C
Temperature resistance (min.):	-20 °C



SDS available on www.kenteurope.com

Terms and Conditions

No part of this publication may be reproduced, transmitted or stored, electronically, mechanically or photocopied without the prior permission of name KENT (United Kingdom) Ltd.
This data sheet and its contents (the "Information") belong to KENT (United Kingdom) Ltd or are licensed to it. No license is granted for the use of it other than for information purposes in connection with the products to which it relates. No license of any intellectual property rights is granted.

The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but the Group assumes no responsibility for its accuracy or completeness, any error from or omission in it nor for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where the Group was

aware of the possibility of such loss or damage arising) is excluded. This will not operate to limit or restrict the Group's liability for death or personal injury resulting from its negligence KENT is the trading name of KENT (United Kingdom) Ltd.
Registered Office: Amber House, Showground Road, Bridgewater, Somerset, United Kingdom TA6 6AJ
All rights reserved

KENT (United Kingdom) Ltd, Forsyth House, Pitreavie Way, Pitreavie Business Park, Dunfermline, Fife KY11 8US

Tel.: 0800 136925 or 01383 723344 between 08:30-17:30 Monday-Thursday, 09:00-15:00 on Fridays'

For out of hours queries please Fax us on 01383 735829 or **Email:** KENTsales.UK@kenteurope.com

2021-06-09